



FUJIAN YAHENG POWER TECHNOLOGY GROUP CO.,LTD

GEL 6GFM125T 12V125AH




6GFM125T is a deep cycle purpose GEL battery . with specially designed for frequent cyclic discharge usage. By using strong grid and specific paste plate, the battery offers 50% more cyclic life than the standby series. It is applicable for power tools, solar & wind energy, telecom system, etc..

Specification

Cells Per Unit	6
Voltage Per Unit	12V
Capacity	125AH@10hr-rate to 1.75V per cell @ 25°C
Weight	Approx. 38.0kg (Tolerance±3%)
Max. Discharge Current	1250A(5sec)
Internal Temperature Range	Discharge: -20°C~60°C Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25±5°C
Float Charging Voltage	13.6 to 13.8 VDC/unit Average at 25°C
Recommended Maximum Charging	37.5A
Equalization and Cycle service	14.4 to 14.8 VDC /unit Average at 25°C
Self Discharge	YAHENG Vale Regulated Lead Acid(VRLA) Can be stored for more than 6 months at 25°C. Self-discharge ratio less than 3% per month at25°C. Please charge batteries before using.
Terminal	Terminal F9
Container Material	A.B.S. UL94-HB, Flammability resistance of UL94-V2 can be avail upon request

Dimensions

Unit: mm Dimension: 565(L)×110(W)×297(H)



Constant Current Discharge Characteristics: A(25°C)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
9.60V	408.2	297.9	243.1	151.0	87.10	52.12	36.02	29.52	24.17	16.65	14.07	7.741.
10.0V	396.4	283.5	238.1	148.5	86.70	51.73	35.89	29.39	24.02	16.51	13.94	7.600
10.2V	384.6	273.4	234.4	147.2	85.89	51.33	35.61	29.25	23.88	169.37	13.80	7.459
10.5V	345.4	252.3	223.1	143.5	85.09	50.94	35.47	28.98	23.60	16.24	13.67	7.318
10.8V	311.8	230.1	205.7	137.2	83.08	50.03	34.51	28.29	23.17	15.97	13.53	7.178
11.1V	266.2	205.6	184.5	128.5	78.93	47.81	32.99	26.93	22.17	15.29	13.13	6.756

Constant Power Discharge Characteristics: W(25°C)


F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
9.60V	4222	3173	2674	1721	1006	614.3	428.7	351.9	288.3	198.7	168.2	92.81
10.0V	4139	3075	2631	1700	1004	611.0	428.8	351.5	287.6	197.8	167.1	91.20
10.2V	4092	2994	2601	1688	996.3	607.4	427.0	350.7	286.6	196.5	165.6	89.51
10.5V	3725	2788	2481	1649	987.4	602.9	425.3	347.4	283.2	194.9	164.0	87.82
10.8V	3393	2570	2294	1580	969.1	595.3	413.7	339.5	278.0	191.6	162.4	86.13
11.1V	2980	2324	2065	1484	927.7	573.2	395.8	323.1	266.1	183.5	157.5	81.07

All mentioned values are average values.




FUJIAN YAHENG POWER TECHNOLOGY GROUP CO.,LTD


Temperature and Valid Capacity




Discharge Characteristics at Various Rates @25°C/77



Charge characteristic curve for standby use



Life characteristics of cyclic use



Discharge Current VS. Discharge Voltage

Final Discharge Voltage V/cell	1.75V	1.75V	1.60V
Discharge Current (A)	A ≤ 0.2C	0.2C ≤ A ≤ 1.0C	≥ 1.0C

Charge the batteries at least once every six months, if they are stored at 25°C

Charging Method:

Constant Voltage	-0.2C*2h+2.4-2.45V/cell*24h, Max.Current 0.3CA
Constant Current	-0.2C*2h+0.1CA*12h
Fast	-0.2C*2h+0.3CA*4.0h

Maintenance & Cautions

Float Service

- ✘ Every month, recommend inspection every battery voltage
 - ✘ Every three months, recommend equalization charge for one time.
- Equalization charge method:
- Discharge: 100% rate capacity discharge.
- Charge: Max. Current 0.3CA, constant voltage 2.4-2.45V/Cell charge 24h
- ✘ Effect of temperature on float charge voltage: -3mV/Cell.
 - ✘ Length of service life will be directly affected by the number of discharge cycles, depth of discharge, ambient temperature and charging voltage.

Contact us:

Fujian Yaheng Power Technology Group Co.,Ltd

Add: Yaheng Industrial Park, Jianyang District, Nanping City, Fujian Province, China

Website: www.yahengpower.com

Email: liwendu@yahengpower.com

Tel: +86-599-5837578 Fax: +86-599-5823986