FUJIAN YAHENG POWER TECHNOLOGY GROUP CO.,LTD

3FM3.2 6V3.2AH

3FM3.2 is a general purpose battery with 5 years floating design life, meet with IEC,JIS standard. With heavy duty grid thickness plates, special additives, FM series battery have long and reliable standby service life.

Specification

Cells Per Unit	3
Voltage Per Unit	6V
Capacity	3.2AH@20hr-rate to 1.75V per cell @ 25℃
Weight	Approx. 0.65kg (Tolerance±3%)
Max. Discharge Current	32A(5sec)
Internal Temperature Range	Discharge: -20℃~60℃ Charge: 0℃~50℃ Storage: -20℃~60℃
Normal Operating Temperature Range	25±5℃
Float Charging Voltage	6.8 to 6.9 VDC/unit Average at 25℃
Recommended Maximum Charging	0.96A Current Limit
Equalization and Cycle service	7.3 to 7.4 VDC /unit Average at 25℃
Self Discharge	YAHENG Vale Regulated Lead Acid(VRLA) Can be stored for more than 6 months at 25℃. Self-discharge ratio less than 3% per month at25℃. Please charge batteries before using
Terminal	Terminal F14/L14
Container Material	A.B.S. UL94-HB, Flammability resistance of UL94-V2 can be avail upon request

Dismensions:



Constant Current Discharge Characteristics: A(25℃)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	5HR	8HR	10HR	20HR
4.80V	13.01	8.531	6.687	3.754	2.230	1.285	0.873	0.580	0.369	0.320	0.180
5.00V	12.54	8.318	6.473	3.706	2.170	1.259	0.857	0.570	0.368	0.317	0.173
5.10V	11.80	7.906	6.293	3.649	2.149	1.245	0.849	0.564	0.365	0.312	0.170
5.25V	10.61	7.393	5.935	3.548	2.107	1.229	0.842	0.557	0.361	0.310	0.165
5.40V	9.508	6.894	5.600	3.431	2.069	1.219	0.832	0.551	0.360	0.305	0.155
5.55V	8.318	6.321	5.166	3.301	2.013	1.170	0.816	0.546	0.357	0.300	0.153

Constant Power Discharge Characteristics: W(25℃)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	5HR	8HR	10HR	20HR
4.80V	136.88	90.74	71.19	42.97	25.90	14.99	10.20	6.868	4.424	3.832	2.152
5.00V	133.32	88.85	70.56	42.52	25.52	14.86	10.18	6.833	4.407	3.796	2.075
5.10V	126.81	85.34	69.63	42.15	25.33	14.76	10.15	6.766	4.374	3.760	2.037
5.25V	115.74	81.82	66.00	41.29	24.99	14.65	10.10	6.686	4.337	3.721	1.979
5.40V	104.42	76.54	62.36	40.32	24.58	14.52	9.986	6.616	4.318	3.664	1.864
5.55V	92.09	71.26	58.73	39.21	24.12	14.02	9.790	6.553	4.288	3.610	1.834

FUJIAN YAHENG POWER TECHNOLOGY GROUP CO.,LTD

Temperature and Valid Capacity



Discharg Characteristics at Various Rates @25℃/77



Charge characteristic curve for standby use



Storage characteristic



Discharge Current VS. Discharge Voltag

Final Discharge Voltage V/cell	1.75V	1.75V	1.60V
Discharge Current (A)	A≤0.2C	0.2C≤A≤1.0C	≥1.0C

Charge the batteries at least once every six months, if they are stored at 25℃

Charging Method:

Constant Voltage	-0.2C*2h+2.4-2.45V/cell*24h, Max.Current 0.3CA
Constant Current	-0.2C*2h+0.1CA*12h
Fast	-0.2C*2h+0.3CA*4.0h

Maintenance & Cautions

Float Service

※ Every month, recommend inspection every battery voltage

※ Every three months, recommend equalization charge for one time.

Equalization charge method:

Discharge: 100% rate capacity discharge.

Charge: Max. Current 0.3CA, constant voltage 2.4-2.45V/Cell charge 24h

※ Effect of temperature on float charge voltage: -3mV/Cell.

※ Length of service life will be directly affected by the number of discharge

cycles, depth of discharge, ambient temperature and charging voltage.

Contact us:

Fujian Yaheng Power Technology Group Co.,Ltd

Add: Yaheng Industrial Park, Jianyang District, Nanping City, Fujian Province, China

Website:www.yahengpower.com

Email:liwendu@yahengpower.com

Tel:+86-599-5837578 Fax:+86-599-5823986